Centro Tessile Serico Sostenibile Srl
via Castelnuovo, 3 - 22100 Como Italia
Pho +39 031 331211
P. IVA - C.F. 03900470133
mailbox@textilecomo.com
www.textilecomo.com

00041

Test Report No.:	**2505028-001**
Date Test Report	**07-ott-25**
Acceptance:	**2505028**
Arrival date sample	**30-set-25**
Start date test	**30-set-25**
End date test	**07-ott-25**
References:	
Sampling Mode:	Sampling by Customer *

Customer Code 08796-1

Dear:
SILENT GLISS FABRICS & COMPONENTS GmbH
Rheinauenstrasse 8
79415 Bad Bellinen Germany
C.a.
Phone:

[C] Item:	**LEVISO LIGHT**
[C] Declared Composition:	**100% Polyester FR**
[C] End use:	**drapery**
[C] Typology:	**fabric**
Return:	**no requested**

Test Results

Test	Method	U.M.	Result
25165 WASHING TREATMENTS	**UNI EN ISO 6330:2022**		.
Start date test 30/09/2025			
End date test 01/10/2025			
Instrument: WASHING-MACHINE ELECTROLUX WASCATOR mod. FOM 71 CLS			
Typology of washing machine used: Type A Programme of washing: 3N - normal agitation Test Temperature: 30°C Drying procedure: type C - Flat dry Detergent used: ECE (ref.A) without optical brightener - Sodium Perborated - TAED Total air-dry- mass (specimens and ballast): 2,0 kg Type of ballast used: Type III (polyester) Number of washings performed: 01			
THE SAMPLE, TREATED AS ABOVE DESCRIBED, HAS BEEN SUBMITTED TO NEXT TEST of CURTAINS AND DRAPES: IGNITABILITY OF VERTICALLY ORIENTED SPECIMENS.			
15386 CURTAINS AND DRAPES: IGNITABILITY OF VERTICALLY ORIENTED SPECIMENS	**UNI EN 1101:2006**		.
Start date test 03/10/2025			
End date test 07/10/2025			
Instrument: Rhoburn Tester			
Pretreatment carried out			1 washing at 30°C
Conditioning of sample			24 h a 20 ± 2 °C, 65 ± 5 % u.r.
Testing temperature and r.h.			19°C, 63% r.h.
Dimension of specimens:		mm	80x200
Type of gas used:			propane
Type of ignition used:			edge ignition

(*) = The tests marked in this way are not accredited by Accredia

The Results contained in this Report refer only to the sample as received and to the objects tested and do not imply an approval of the tested product by the Laboratory of the Centro Tessile Serico Sostenibile Srl. Unless otherwise specified, the side examined / straight of use is indicated by the Customer: this information can influence the results of the tests and therefore the Test Laboratory declines all responsibility.
This Report may not be reproduced in part, unless written permission of Centro Tessile Serico Sostenibile Srl Laboratory.
[C] = Information provided by the Customer, of which the Centro Tessile Serico Sostenibile Srl Laboratory declines all responsibility.

Centro Tessile Serico Sostenibile Srl
via Castelnuovo, 3 - 22100 Como Italia
Pho +39 031 331211
P. IVA - C.F. 03900470133
mailbox@textilecomo.com
www.textilecomo.com

00041

Test Report No.: **2505028-001**

Test	Method	U.M.	Result
MEAN IGNITION TIME			SAMPLE DOES NOT BURN AT 20s OF APPLICATION TIME OF THE FLAME
Deviations from the method			none
Annex n.			1F
Details of the test results related to each specimen can be seen in the annex of this test report.			
25165 WASHING TREATMENTS	**UNI EN ISO 6330:2022**		.
Start date test 30/09/2025 **End date test** 02/10/2025 **Instrument:** WASHING-MACHINE ELECTROLUX WASCATOR mod. FOM 71 CLS Typology of washing machine used: Type A Programme of washing: 3N - normal agitation Test Temperature: 30°C Drying procedure: type C - Flat dry Detergent used: ECE (ref.A) without optical brightener - Sodium Perborated - TAED Total air-dry- mass (specimens and ballast): 2,0 kg Type of ballast used: Type III (polyester) Number of washings performed: 12 THE SAMPLE, TREATED AS ABOVE DESCRIBED, HAS BEEN SUBMITTED TO NEXT TEST of BURNING BEHAVIOUR - CURTAINS AND DRAPES - Measurement of flame spread of vertically oriented specimens with large ignition source.			
15676 BURNING BEHAVIOUR - CURTAINS AND DRAPES - Measurement of flame spread of vertically oriented specimens with large ignition source	**UNI EN 13772:2011**		.
Start date test 03/10/2025 **End date test** 07/10/2025 **Instrument:** Rhoburn Tester			
Conditioning of sample			24 h a 20 ± 2 °C, 65 ± 5 % u.r.
Testing temperature and r.h.			19°C, 63% r.h.
TEST ON SAMPLE IN ITS ORIGINAL STATE:			.
- severing of marker threads		-	none
Evidence of flaming debris		-	none
TEST ON REFURBISHED SAMPLE:			.
- severing of marker threads		-	none
Evidence of flaming debris		-	none
Deviations from the method			none
Annex n.			2F
Details of the test results related to each specimen can be seen in the annex of this test report.			

(*) = The tests marked in this way are not accredited by Accredia

The Results contained in this Report refer only to the sample as received and to the objects tested and do not imply an approval of the tested product by the Laboratory of the Centro Tessile Serico Sostenibile Srl. Unless otherwise specified, the side examined / straight of use is indicated by the Customer: this information can influence the results of the tests and therefore the Test Laboratory declines all responsibility.
This Report may not be reproduced in part, unless written permission of Centro Tessile Serico Sostenibile Srl Laboratory.
[C] = Information provided by the Customer, of which the Centro Tessile Serico Sostenibile Srl Laboratory declines all responsibility.

Centro Tessile Serico Sostenibile Srl
via Castelnuovo, 3 - 22100 Como Italia
Pho +39 031 331211
P. IVA - C.F. 03900470133
mailbox@textilecomo.com
www.textilecomo.com

00041

Test Report No.: **2505028-001**

Test	Method	U.M.	Result
15986 TEXTILES AND TEXTILE PRODUCTS - BURNING BEHAVIOUR - CURTAINS AND DRAPES - CLASSIFICATION SCHEME	**EN 13773:2004**		CLASS 1

The fabric tested according to standards
UNI EN 1101: 2006 "Textiles and textile products. Burning behaviour. Curtains and drapes. Detailed procedure to determine the ignitability of vertically oriented specimens (small flame)" and
UNI EN 13772: 2011 "Textiles and textile products. Burning behaviour. Curtains and drapes. Measurement of flame spread of vertically oriented specimens with large ignition source"

MEETS THE REQUIREMENTS OF CLASS 1 according to the UNI EN 13773: 2004"Textiles and textile products - Burning behavior - Curtains and drapes - Classification scheme"

The Laboratory Manager
Fausto Albonico

END OF REPORT

(*) = The tests marked in this way are not accredited by Accredia

The Results contained in this Report refer only to the sample as received and to the objects tested and do not imply an approval of the tested product by the Laboratory of the Centro Tessile Serico Sostenibile Srl. Unless otherwise specified, the side examined / straight of use is indicated by the Customer: this information can influence the results of the tests and therefore the Test Laboratory declines all responsibility.
This Report may not be reproduced in part, unless written permission of Centro Tessile Serico Sostenibile Srl Laboratory.
[C] = Information provided by the Customer, of which the Centro Tessile Serico Sostenibile Srl Laboratory declines all responsibility.